

Technical Data Specification Sheet

Flash PE Packed 8U Clay Desiccant

Product Flash PE Packed 8U Clay Desiccant

Product Code 2MTKP307A

Raw Material 1~4mm Montmorillonite

Packaging Material Flash PE

Technical Standard

| Items | | Standard |
|---|--------|--|
| Appearance | | The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains. |
| Loss on Drying | | ≤2.0% |
| Unit Moisture adsorption capacity 25°C | RH=20% | ≥2.85g |
| | RH=40% | ≥5.70g |
| Unit Moisture adsorption rate 25°C | RH=40% | ≥0.25g/7h |
| | RH=80% | ≥0.7g/7h |
| Particle Size (12.5~0.177mm) | | ≥96.0% |
| Dust Permeability Per Unit | | < 0.5mg |
| Corrosiveness 25°C RH=60% ≥24h | | Non-corrosive |
| Dropping resistance | | In the case of free falling of 20 times at a height of 3m, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak. |

Pouch Dimension

| | |
|---------------|----------|
| Gross Weight: | 279~293g |
| Width: | 150±8mm |
| Length: | 180±9mm |

Sealing Method Back Seal

Printing Wisesorbent



Technical Data Specification Sheet

Flash PE Packed 8U Clay Desiccant

STD Packaging — 300pcs/PE bag/drum
Drum Dimension: ϕ 450×890 mm 5drums/pallet
—Drum label contains the following:
PO Number
Product Name
Specification
Quantity
Batch Number
MADE IN USA

Storage Shelf life: 2 years
Desiccant must always be kept in airtight containers to avoid moisture.

Notes The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable for his own operation.

2023-02-14

