

## **Technical Data Specification Sheet**

## Tyvek packed 14g Molecular Sieve Desiccant

**Product** Tyvek packed 14g Molecular Sieve Desiccant

**Product Code** 1MSTY008A

**Raw Material** 0.5~1.0mm 4A molecular sieve

**Packaging** 

Material

Uncoated Tyvek

Technical	

Standard

Items		Standard
Appearance		The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains. The transparency of the back seal for each pack of product should be more than 50%.
Loss on Drying (575±25℃)		≤4.5%
Moisture adsorption capacity 25°C	RH=40%	≥15.0%
	RH=80%	≥16.5%
Dropping resistance		In the case of free falling of 15 times at a height of 1.2m or more, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak.
Decoloring test		The soaked solution should be colorless.
Total residual solvents		$\leq 5 \text{mg/m}^2$
Benzene residues		Not detectable
* Lead		≤5ppm
Paper bag fluorescence		No flaky fluorescence
Total bacterial count (cfu / bag)		$\leq 10^{3}$
Mould and yeast count (cfu / bag)		$\leq 10^{2}$
Escherichia coli		Not detectable per bag

Sachet Dimension Net Weight: Width:

13.3~15.4g

Length:

38±2mm 90±5mm

**Sealing Method** 

Melting Seal

**Printing** 

Wisemini





## **Technical Data Specification Sheet**

## Tyvek packed 14g Molecular Sieve Desiccant

**STD Packaging** — 500pcs/PE/drum

Drum Size:  $\phi$  275\*345mm, 48drums/pallet

—Carton label contains the following:

PO Number Product Name Specification Quantity

Batch Number MADE IN USA

**Storage** Shelf life: 2 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes The data given here is based on current knowledge and experience. This document is

designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable

for his own operation.

2023-02-14

