

Technical Data Specification Sheet

Flash PE packed 3g Molecular Sieve Strip Desiccant

Product Flash PE packed 3g Molecular Sieve Strip Desiccant

Product Code 1MSTY104A

Raw Material 0.5~1.0mm 4A molecular sieve

Packaging

Material

Technical Standard Uncoated Tyvek

Items		Standard	
Appearance		The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains. The transparency of the back seal for each pack of product should be more than 50%.	
Loss on Drying (575±2	25°C)	≤4.5%	
Moisture adsorption capacity	RH=40%	≥15.0%	
25°C	RH=80%	≥16.5%	
Dropping resistance	e	In the case of free falling of 15 times at a height of 1.2m or more, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak.	
Decoloring test		The soaked solution should be colorless.	
Total residual solver	nts	$\leq 5 \text{mg/m}^2$	
Benzene residues		Not detectable	
* Lead		≤5ppm	
Paper bag fluorescen	ice	No flaky fluorescence	
Light transmittance (cont	inuous)	≥2000	
Total bacterial count (cfu	ı / bag)	≤10 ³	
Mould and yeast count (cf	fu / bag)	≤10 ²	
Escherichia coli		Not detectable per bag	

Sachet

Net Weight:

2.80~3.20g

Dimension

26±1mm

Width: Length:

56±2mm

Sealing Method

Ultrasonic Seal

Printing

Wisemini





Technical Data Specification Sheet

Flash PE packed 3g Molecular Sieve Strip Desiccant

STD Packaging —3500pcs/roll/PE/foil bag/ctn

Each roll with one pcs of 8% HIC

Roll size $295\times2\times77.5$ mm Baffle size $\Phi355\times5$ m

Roll cap size match 76mm hole

Pearl pad size $\phi 140 \times 6mm$ PE bag size $650 \times 650mm$ Foil bag size $620 \times 800mm$ Carton size $370 \times 370 \times 340mm$

— product label contains below:

Manufacturer Product Description

Quantity per carton

Batch No.

Storage Shelf life: 2 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable

for his own operation.

2023-02-14

