

## **Technical Data Specification Sheet**

## Flashed PE packed 3g Silica Gel Mixed Active Carbon Desiccant Deodorizer Strip

**Product** Flashed PE packed 3g Silica Gel Mixed Active Carbon Desiccant Deodorizer Strip

**Product Code** 2ASTG204A

Raw Material 0.5~2mm irregular Silica Gel

0.5~2mm active carbon 50%

**Packaging** 

Material Tyvek

Items		Standard
Appearance		The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains.
Loss on Drying(150 $^{\circ}$ C)		≤5.0%
Moisture adsorption capacity 25°C	RH=40%	≥10.0%
	RH=80%	≥24.0%
Dropping resistance		In the case of free falling of 15 times at a height of 1.2m or more, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak.
Carbon Tetrachloride Adsorption		≥30%
Decoloring test		The soaked solution should be colorless.
Iodine value		≥ 500 mg/g

50%

Technical Standard

Sachet Weight:  $2.80\sim3.30$ g

Dimension Width:  $25\pm1$ mm

Length:  $65\pm3$ mm

Sealing Method Back Seal With Hole

**Printing** Wisemini





## **Technical Data Specification Sheet**

## Flashed PE packed 3g Silica Gel Mixed Active Carbon Desiccant Deodorizer Strip

**STD Packaging** —2000pcs/roll/PE/foil bag/ctn

Each roll with one pcs of 8% HIC

Roll size  $295\times2\times77.5$ mm Baffle size  $\Phi355\times5$ m Roll cap size match 76mm hole

Roll cap size match 76mm ho

Pearl pad size φ140×6mm

PE bag size  $650 \times 650 \text{mm}$ , 3s Foil bag size  $650 \times 800 \text{mm}$ Carton size  $370 \times 370 \times 340 \text{mm}$ 

— product label contains below:

Manufacturer Product Description

Quantity per carton

Batch No.

MADE IN USA

Storage

Shelf life: 2 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable for his own operation.

2023-02-14

