

Technical Data Specification Sheet

Flash PE packed 10g Molecular Sieve Strip Desiccant

Product Flash PE packed 10g Molecular Sieve Strip Desiccant

Product Code 2MSTG207A

Raw Material 0.5~1.0mm 4A molecular sieve

Packaging

Material

Flash PE

Technical Standard

Items		Standard		
Appearance		The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains.		
Loss on Drying (575 \pm 2	25℃)	≤4.5%		
Moisture adsorption capacity	RH=40%	≥15.0%		
25°C	RH=80%	≥16.5%		
Dropping resistance	e	In the case of free falling of 15 times at a height of 1.2m or more, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak.		
Decoloring test		The soaked solution should be colorless.		
Total residual solver	its	≤5mg/m ²		
Benzene residues		Not detectable		
* Lead		≤5ppm		
Paper bag fluorescen	ce	No flaky fluorescence		
Total bacterial count (cfu	/bag)	$\leq 10^{3}$		
Mould and yeast count (cf	u / bag)	≤10 ²		
Escherichia coli		Not detectable per bag		

Sachet Dimension Net Weight: Width:

9.5~11.0g

T 41

37±2mm

Length:

88±4mm

Sealing Method

Back Seal With Hole

Printing

Wisemini





Technical Data Specification Sheet

Flash PE packed 10g Molecular Sieve Strip Desiccant

STD Packaging —1000pcs/roll/PE/foil bag/ctn

Each roll with one pcs of 8% HIC

Roll size $295\times2\times77.5$ mm Baffle size $\Phi355\times5$ m

Roll cap size match 76mm hole Pearl pad size ϕ 140×6mm PE hag size 650×650mm 3s

PE bag size $650 \times 650 \text{mm}$ 3s Foil bag size $650 \times 800 \text{mm}$ Carton size $370 \times 370 \times 340 \text{mm}$

— product label contains below:

Manufacturer Product Description

Quantity per carton

Batch No.

MADE IN USA

Storage

Shelf life: 2 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable for his own operation.

2023-02-14

