

## **Technical Data Specification Sheet**

## 3g Canister Desiccant

**Product** 3g Canister Desiccant

**Product Code** 6SGPL503A

Raw Material Type A, 1~3mm beaded Silica Gel

Packaging

Plastic Shell

Material

| Items                             |        | Standard   |
|-----------------------------------|--------|--|
| Appearance                        |        | Shell should be in perfect condition without broken; Laser should be clear and no stains.  |
| Loss on Drying                    |        | ≤3.0%  |
| Moisture adsorption capacity 25°C | RH=40% | ≥19.0%   |
|                                   | RH=80% | ≥27.0%   |
| Dropping resistance               |        | In the case of free falling of 15 times at a height of 1m or more, the plastic shell shall not be broken and the adsorbent shall not leak. |
| Decoloring test                   |        | The soaked solution should be colorless.   |
| Total residual solvents           |        | ≤5mg/m²  |
| * Lead                            |        | ≤5ppm  |
| Fiber sheet fluorescence          |        | No flaky fluorescence  |
| Total bacterial count (cfu / bag) |        | $\leq 10^{3}$  |
| Mould and yeast count (cfu / bag) |        | ≤10 <sup>2</sup>   |
| Escherichia coli                  |        | Not detectable per bag   |

Technical Standard

SachetNet Weight:2.8~3.3gDimensionGross Weight:4.6~5.1gDiameter:19.5±0.5m

Diameter:  $19.5\pm0.5$ mm Height:  $25.5\pm0.5$ mm

**Printing** WISECAN

DO NOT EAT





## **Technical Data Specification Sheet**

## **3g Canister Desiccant**

**STD Packaging** — 1200pcs/PE/drum

Drum Size: φ 275\*345mm, 63drums/pallet

—Carton label contains the following:

PO Number Product Name Specification Quantity

Batch Number MADE IN USA

**Storage** Shelf life: 2 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do

not imply any guarantee concerning composition, properties or performance. User is liable

for his own operation.

2023-02-14

