

Technical Data Specification Sheet

TBM41 Molecular Sieve Tablet

Product TBM41 Molecular Sieve Tablet

Product Code TBM41A

Raw Material 4A Molecular sieve powder

Technical Standard

Items		Standard
Appearance		The surface of desiccant should not have obvious defect.
Loss on Drying (575±25℃)		≤3.0%
Moisture adsorption capacity 25°C	RH=20%	≥15.0%
	RH=40%	≥18.0%
Moisture adsorption speed		≥10.0%/24h
Dust		≤0.3mg/g

Sachet **Dimension** Net Weight:

 $0.235 \pm 0.015g$

Diameter: Height:

6.00±0.06mm 7.40±0.35mm

Molding

Tablet

Method

STD Packaging

— 7000pcs/PE/tin 28000pcs/4 tins/carton

Carton Size: 350×350×180 mm, 45ctns/pallet

—Carton label contains the following:

PO Number **Product Name** Specification Quantity

Batch Number

Storage

Shelf life: 3 years

Desiccant must always be kept in airtight containers to avoid moisture.

Notes

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable

for his own operation.