

Technical Data Specification Sheet

TBM61 Molecular Sieve Tablet

Product Code TBM61A

Raw Material 4A Molecular sieve powder

| | Items | | | Standard |
|-----------------------|--|--------------------------------------|------|--|
| Technical Standard | Appearance | | | The surface of desiccant should not have obvious defect. |
| | Loss on Drying $(575\pm25^{\circ}C)$ | | | ≤3.0% |
| | Moisture adsor | Moisture adsorption capacity 25°C | | ≥15.0% |
| | | | | ≥18.0% |
| | Moistur | Moisture adsorption sp | | ≥10.0%/24h |
| | | Dust | | ≤0.3mg/g |
| | | | | |
| Sachet | Net Weight: | 0.066 ± 0.0 | 009g | |
| Dimension | Diameter: | 3.50±0.05mm | | |
| | Height: | 6.00±0.30 | mm | |
| | | | | |
| Molding | Tablet | | | |
| Method | | | | |
| STD Packaging | 20000pcs/PE/tin 80000pcs/4 tins/carton Carton Size: 350×350×180 mm, 45ctns/pallet Carton label contains the following: PO Number Product Name Specification Quantity Batch Number | | | |
| Storage | Shelf life: 3 years Desiccant must always be kept in airtight containers to avoid moisture. | | | |
| Notes | The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable | | | |

2023-02-14

for his own operation.

