

Technical Data Specification Sheet

Flash PE packed 3g Silica Gel Strip Desiccant

Product Flash PE packed 3g Silica Gel Strip Desiccant

Product Code 1SGTY104A

Raw Material Type A 0.5~2mm irregular Silica Gel

Packaging

Material

Flash PE

Technical
Standard

Items		Standard
Appearance		The surface of desiccant bag should not have damage or obvious discoloration, with the flat paper. The printing is clear without stains. The transparency of the back seal for each pack of product should be more than 50%.
Loss on Drying		≤3.0%
Moisture adsorption capacity 25°C	RH=40%	≥19.0%
	RH=80%	≥27.0%
Dropping resistance		In the case of free falling of 15 times at a height of 1.2m or more, the desiccant bag shall not be broken or have the damage of enabling the adsorbent to leak.
Decoloring test		The soaked solution should be colorless.
Total residual solvents		≤5mg/m²
Benzene residues		Not detectable
* Lead		≤5ppm
Paper bag fluorescence		No flaky fluorescence
Light transmittance (continuous)		≥2000
Total bacterial count (cfu / bag)		≤10³
Mould and yeast count (cfu / bag)		≤10 ²
Escherichia coli		Not detectable per bag

Sachet

Net Weight:

2.80~3.20g

Dimension

Width: 26 ± 1 mm

Length:

60±3mm

Sealing Method

Ultrasonic Seal

Printing

Wisemini





Technical Data Specification Sheet

Flash PE packed 3g Silica Gel Strip Desiccant

STD Packaging —3500pcs/roll/PE/foil bag/ctn

Each roll with one pcs of 8% HIC

Roll size $295 \times 2 \times 77.5$ mm Baffle size $\Phi 355 \times 5$ m

Roll cap size match 76mm hole

Pearl pad size φ140×6mm

PE bag size $650 \times 650 \text{mm}$, 3s Foil bag size $620 \times 800 \text{mm}$ Carton size $370 \times 370 \times 340 \text{mm}$

— product label contains below:

Manufacturer Product Description

Quantity per carton

Batch No.

Storage Shelf life: 2 years

Notes

Desiccant must always be kept in airtight containers to avoid moisture.

The data given here is based on current knowledge and experience. This document is designed to describe the products in terms of their safety requirements. The above details do not imply any guarantee concerning composition, properties or performance. User is liable

for his own operation.

2023-02-14

